

CERTIFICATE OF COMPLIANCE
Material and Production Test Certification
Mueller 4-12" A2361 Resilient Wedge Gate Valves

Date: 6/27/17

WE HEREBY CERTIFY that MUELLER CO. 4-12" A2361 Series RWGV's are manufactured and tested at the Mueller ISO 9001 registered facility in Chattanooga, TN, USA. Mueller certifies these valves are UL 262 Listed, FM 1120/1130 Approved, are certified to ANSI/NSF 61 & 372 and meet the requirements of AWWA C515. Production testing is performed in accordance with these standards and meets the following specifications.

Size	Model No.	AWWA (psi)	UL (psi)	FM* (psi)	Hydro Seat Test (psi)	Hydro Shell Test (psi)
4-12"	A2361	350	350	350	525/525	700

* NOTE: FM only approves Open Left valves.

Mueller certifies that the valve body, bonnet and wedge are manufactured in a Mueller foundry in Albertville, AL or Chattanooga, TN per Mueller QA procedures; each heat is tested and certified to be within the specification shown in the chart below under a controlled program and in accordance with ASTM A536 Ductile Iron.

Ductile Iron: ASTM A536										
CHEMICAL COMPOSITION										
Element	C	Si	Mn	S	Cu	P	Cr	Ti	Pb	Mo
Minimum	3.900	2.500	0.370	-----	0.140	-----	-----	-----	-----	-----
Maximum	3.950	2.800	0.420	0.022	0.180	0.050	0.080	0.015	0.005	-----

Mueller certifies that manganese bronze stems are manufactured under a controlled program and are in accordance with ASTM B138.

Manganese Bronze ASTM B138; Alloy C67600 (H04)									
Chemical Composition							Mechanical Properties		
Element	Cu	Fe	Pb	Mn	Sn	Zn	Tensile	Yield	Elongation
Minimum	57.00	0.40	0.50	0.05	0.50	Remainder	76,000	52,000	10.00%
Maximum	60.00	1.30	1.00	0.50	1.50	Remainder	-----	-----	-----

Mueller certifies that valves wedges are encapsulated with SBR rubber manufactured under a controlled program and is in accordance with Mueller Rubber Specification R-88.

SBR (Mueller Rubber Specification R-88); ASTM D2000				
Specification	Durometer	Tensile	Elongation	Compression Set
Minimum	73	2,000	200%	0.00
Maximum	83	----	----	18.00

Mueller certifies the coating supplied with these valves is Mueller® Pro-Gard™ Epoxy Coating, an exceptional fusion bonded epoxy electrostatically applied to valve internal and external surfaces to protect against corrosion. This coating is Sienna red in color, non-toxic and suitable for use with drinking water components. Mueller valves with Pro-Gard are certified to NSF 61 & 372 and meet or exceed AWWA C550 requirements. Valves have a standard coating of ten mils nominal thickness.

Mueller certifies that components for A2361 RWGV's are manufactured in accordance with Mueller Co. QA procedures which include but are not limited to relevant dimensional, visual, and functional inspection and verification.

Respectfully,



Anton Nasledov
 Product Manager - Water Products Division
 Mueller Company
 1401 Mueller Avenue, Chattanooga, TN 37406
 Email: anasledov@muellercompany.com
 Website: www.muellercompany.com